



## Top Floor PU 2020-SL

### Product Description

It is a self-leveling, flame retarder, two component hard elastic, thick layer polyurethane coating with high impact and abrasion resistance to acidic and basic solutions. The product can be applied in a thickness of 2-3 mm. This product is 100% solids, aromatic polyurethane-based resin that provides a seamless, wearing suitable for the traffic of wheeled vehicles.

### Product uses:

- Traffic areas as garages, car parks, or industrial floorings.
- Floorings of high decontamination and cleaning requirements in the chemical and food industries.
- Marine floors.

### Properties

- Solvent Free
- Flame retarder
- High impact resistance
- Chemical resistance
- Self-leveling.

### TECHNICAL PROPERTIES

<i>Appearance/Color</i>	High Glass / RAL Color Card
<i>Density:</i>	1.30 kg/liter
<i>Volume solids %:</i>	100 %
<i>Theoretical spreading rate:</i>	0.5 m <sup>2</sup> /ltr / 0.38 m <sup>2</sup> /kg (2000 micron DFT)
<i>Recommended DFT: (Dry Film thickness)</i>	1 - 2 mm per coat
<i>Flash Point:</i>	22° C. / 71.6 °F
<i>Open time:</i>	1.5 hours (23°C and 50% R.H.)
<i>Surface dry:</i>	1 - 2 approx. hour(s) 23°C/73.4°F 50% R.H
<i>Light foot traffic</i>	12-18 hours (23°C and 50% R.H.)
<i>Full dry:</i>	24 hours (23°C and 50 % R.H.)
<i>Full cure time:</i>	7 days (23°C and 50 % R.H.)
<i>Application temperature:</i>	+8 °C/46.4° F and +35 °C/ 95°F
<i>Min. cure temperature:</i>	+10°C/50°F

### Application Details

<i>Mixing Ratio:</i>	Component 4 – Component B: 1 (By weight)
<i>Application method:</i>	Metal Trowel
<i>Thinner:</i>	Polyurethane Thinner
<i>Thinner Amount:</i>	Do not thin



## **Surface Preparation:**

- Surface must be dry, clean and free of all contamination such as dirt, oil, grease, and coatings etc. which hinder adhesion.
- Surface must be firm and have enough strength. If in doubt, apply a test area before beginning.
- Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.
- All dust, loose and friable particles should be removed from the surface before application with brush and/or vacuum cleaner.
- Grinding by diamond disk should take over the place and all the dust must be removed by vacuum machine.
- All the cracks must be repaired by epoxy filler or epoxy mortar.
- A and B components should be thoroughly mixed for 3-4 minutes in order to achieve a homogenous mix using a low speed electric stirrer or other suitable equipment until a homogenous mixture has been achieved. After mixing, primer is ready for application.

## **PRECEDING COAT:**

- **Top Floor 600-SF**
- **Top Floor TS 650-MT**

## **Important Remarks:**

- Surfaces must have enough structural strength.
- Concrete should have minimum of 25 N/mm<sup>2</sup> compression resistance and minimum 1, 5 N/mm<sup>2</sup> tensile strength.
- Applications below 10°C should be avoided.
- High temperatures lower the pot life of the product, while low temperatures extend cure time and consumption.
- Be careful about product mixing ratios.
- The surface should be protected from moisture and rain for 8-10 hours after application.
- All application tools and equipment should be cleaned with thinner immediately after the use. Cured material can only be removed mechanically.
- Use only where application and drying can proceed at temperatures above: 10°C/50°F. The temperature of paint itself should be 15°C/59°F or above. Apply only on a dry and clean surface with a Temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

## **Shelf life & Storage:**

12 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

## **Safety:**

For information and precautions on the safe handling, transportation storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.



***Legal Notice:***

The information presented herein is given in good faith but without warranty. It's based on our experience, indicates our laboratory work results and does not necessarily indicate final product performance. We cannot be held liable for the results obtained with our products and for any loss or accident that may result from its use. Our suggestions don't release you from the obligation to check their validity and to test our products for both your process and end use application. All our products are sold in accordance with our General Conditions of Sale. We don't make any warranty, express or implied, including but not limited to the merchant ability and fitness for a particular purpose.