



## Top Floor SL 1000

### Product Description

High quality self-leveling Flow applied three component coating for application to new and existing concrete & metal floors. It provides smooth, easily cleaned surfaces which is resistant to dirt, moisture, oil, and light-medium abrasion and chemical attack.

### Product uses:

- Factory floors
- Food/hygiene e.g. Abattoirs,/milking parlous
- Car plants
- Hospitals
- Garages
- Laboratories

### Properties

- Durable - good resistance to abrasion and impact.
- Economical - easy to apply, minimizes cleaning costs.
- Fast - Can be applied on green concrete.
- Water miscible - safe in use, no odor.
- Longevity - Good abrasion and corrosion resistance.
- Attractive - available in a range of colors.
- Environment friendly - No V.O.C.
- Good resistance to a wide range of chemicals.
- None tainting.

### TECHNICAL PROPERTIES

<i>Appearance/Color</i>	Glossy / RAL Color Card
<i>Density:</i>	1.65 kg/liter (Mixed)
<i>Volume solids %:</i>	100 %
<i>Theoretical spreading rate:</i>	1 m <sup>2</sup> /ltr / 0.60 m <sup>2</sup> /kg (1mm DFT)
<i>Consumption:</i>	1 ltr/ m <sup>2</sup> ( 1.65 kg/m <sup>2</sup> )
<i>Recommended DFT:</i> <i>(Dry Film thickness)</i>	1 mm
<i>Flash Point:</i>	130°C. /266 °F.
<i>Open time:</i>	2 hours (23°C and 50% R.H.)
<i>Surface dry:</i>	2 approx. hour(s) 23°C/73.4°F 50% R.H
<i>Light foot traffic</i>	14-18 hours (23°C and 50% R.H.)
<i>Full dry:</i>	24 hours (23°C and 50 % R.H.)
<i>Full cure time:</i>	7 days (23°C and 50 % R.H.)
<i>Application temperature:</i>	+8 °C/46.4° F and +35 °C/ 95°F
<i>Min. cure temperature:</i>	+10°C/50°F



## Application Details

<i>Mixing Ratio:</i>	Component A: 4.6– Component B: 2 - Component C: 9.4 (By weight) Component A: 8.62 – Component B:3.75 – Component C:17.62
<i>Application method:</i>	Metal Trowel
<i>Thinner:</i>	Do Not Thin The Product
<i>Thinner Amount:</i>	Do Not Thin the product

<b><i>Sulphuric Acid30 %:</i></b>	Excellent
<b><i>Sodium Hydroxide 25%</i></b>	Excellent
<b><i>Engine Oil:</i></b>	Excellent
<b><i>Lactic Acid 25%:</i></b>	Good
<b><i>Ammonia Solution 25%:</i></b>	Good
<b><i>Citric Acid 25%:</i></b>	Good
<b><i>Petrol:</i></b>	Excellent
<b><i>Sugar Solution 40%:</i></b>	Good
<b><i>Hydrochloric Acid 30%:</i></b>	Excellent

## Surface Preparation:

- Surface must be dry, clean and free of all contamination such as dirt, oil, grease, and coatings etc. which hinder adhesion.
- Surface must be firm and have enough strength. If in doubt, apply a test area before beginning.
- Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.
- All dust, loose and friable particles should be removed from the surface before application with brush and/or vacuum cleaner.
- Grinding by diamond disk should take over the place and all the dust must be removed by vacuum machine.
- All the cracks must be repaired by epoxy filler or epoxy mortar.
- A and B components should be thoroughly mixed for 2-3 minutes and then Component C is added gradually in order to achieve a homogeneous mix using a low speed electric stirrer or other suitable equipment until a homogeneous mixture has been achieved.

## **PRECEDING COAT:**

- Top Floor 600-SF
- Top Floor FB 700
- Top Floor TS 650-MT
- Top Floor TS 700-WB



## Important Remarks:

- Surfaces must have enough structural strength.
- Concrete should have minimum of 25 N/mm<sup>2</sup> compression resistance and minimum 1, 5 N/mm<sup>2</sup> tensile strength.
- Applications below 10°C should be avoided.
- High temperatures lower the pot life of the product, while low temperatures extend cure time and consumption.
- Be careful about product mixing ratios.
- The surface should be protected from moisture and rain for 8-10 hours after application.
- All application tools and equipment should be cleaned with thinner immediately after the use. Cured material can only be removed mechanically.
- Use only where application and drying can proceed at temperatures above: 10°C/50°F. The temperature of paint itself should be 15°C/59°F or above. Apply only on a dry and clean surface with a Temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

## Shelf life & Storage:

24 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

## Safety:

For information and precautions on the safe handling, transportation storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## Legal Notice:

The information presented herein is given in good faith but without warranty. It's based on our experience, indicates our laboratory work results and does not necessarily indicate final product performance. We cannot be held liable for the results obtained with our products and for any loss or accident that may result from its use. Our suggestions don't release you from the obligation to check their validity and to test our products for both your process and end use application. All our products are sold in accordance with our General Conditions of Sale. We don't make any warranty, express or implied, including but not limited to the merchant ability and fitness for a particular purpose.

